

## Production Range

Solid Chipboard

Board Thick mm	Pressing Width a : Production Arnberg; g : Gotha; [...]: Non-Standard mm				Weight									
					VT		VL		VV		Others			
					kg/m <sup>2</sup>	kg/m <sup>3</sup>	kg/m <sup>2</sup>	kg/m <sup>3</sup>	kg/m <sup>2</sup>	kg/m <sup>3</sup>	Typ	kg/m <sup>2</sup>	kg/m <sup>3</sup>	
<b>Solid Chipboard</b>														
10	1220	1250 <sub>g</sub>		2020 <sub>a</sub>			5,6	560	6,6	660				
10,6	1220	[1880]		2020 <sub>g</sub>			5,9	560	6,7	630				
11	1220 <sub>a</sub>			2020			6,2	560	6,9	630				
12	1220	1880		2020 <sub>g</sub>			6,7	560	7,8	650				
13	1220			2040 <sub>g</sub>			7,3	560	8,4	645				
13,5				2040 <sub>g</sub>			7,6	560						
14,3				2040 <sub>g</sub>			8,0	560						
16		1880		2020 <sub>g</sub>			8,3	520						
16,5		[1880]	2020	[2070]			8,6	520	10,4	630				
19			1978 <sub>g</sub>			8,0	420	9,9	520					
25		[1250]		2070 <sub>a</sub>			13,0	520	15,8	630	VS	13,5	540	
28	[955]	1270 <sub>a</sub>	[1880]	1975	2042	11,8	420	14,0	500	17,6	630	VS	15,1	540
32	1265	1880 <sub>a</sub>	1888 <sub>g</sub>	[1940]	2090 <sub>a</sub>	13,4	420	15,7	490	9,2	600			
33	1265	1880	1958	[2000]	2090	13,9	420	16,2	490	19,8	600	VS	17,8	540
33,5	1265 <sub>a</sub>		1958 <sub>g</sub>		2090 <sub>g</sub>	14,1	420	16,4	490					
34	1260 <sub>a</sub>	[1265]	[1880]	1958 <sub>g</sub>	2090	14,3	420	16,7	490	20,4	600			
35		[1880]	[1958]			14,7	420	17,5	490	21,0	600	VS	18,2	520
38			1920	1978		16,0	420	18,6	490	23,6	620	VE	20,1	530
												VE1	19,4	510
												VE7	17,9	470
42				1978				20,6	490					
							HVA		HVB					

### Stile Material „HOMOGENEOUS WOOD“

28				2042 <sub>a</sub>		8,2	650							
32	1880 <sub>a</sub>			2040 <sub>a</sub>	2090 <sub>a</sub>	20,8	650	22,4	700					
33		1958 <sub>a</sub>	[2000]	2040 <sub>a</sub>	2090 <sub>a</sub>	21,5	650	23,1	700					
34					2090 <sub>a</sub>	22,1	650	23,8	700					

### Length

Pressing width < 1270 mm : 600 - 3000 mm

Pressing width > 1270 mm : 600 - 1200 mm