

Extruded particleboards — Specifications

Strangpressplatten — Anforderungen

Panneaux de particules extrudés — Exigences

	Contents	Page
ICS:	Foreword	3
Descriptors:	1 Scope	3
	2 Normative references	3
	3 Terms and definitions	5
	4 Symbols and abbreviations	5
	5 Requirements	5
	5.1 General requirements	6
	5.2 Mechanical properties	6
	6 Supplementary properties	7
	7 Factory production control	7
	8 Marking	8
	Annex A (normative) Test methods of bending strength, internal bond and dimensional variations	9
	A.1 Bending strength	9
	A.1.1 Principle	9
	A.1.2 Sampling and dimensions of test pieces	9
	A.1.3 Apparatus	9
	A.1.4 Procedure	9
	A.1.5 Expression of results	9
	A.2 Tensile strength	9
	A.2.1 Principle	9
	A.2.2 Sampling and dimensions of test pieces	10
	A.2.3 Apparatus	10
	A.2.4 Procedure	11
	A.2.5 Expression of results	11
	A.3 Dimensional variations	11
	A.3.1 Principle	11
	A.3.2 Sampling	11
	A.3.3 Apparatus	11
	A.3.4 Procedure	11
	A.3.5 Expression of results	11
	Annex B (informative) Supplementary properties	12
	Bibliography	13

Document type: European Standard

Document subtype:

Document stage: Formal Vote

Document language: E

Detail DIN EN 14755

Minimum values of mechanical properties:

Board type	Thickness range (mm)	Bending strength perpendicular to fabrication (N/mm ²)	Tensile strength parallel to fabrication (N/mm ²)
ES	≤ 16 $> 16 \leq 50$	4 3	0,17 0,17
ET	≤ 30 $> 30 \leq 45$ $> 45 \leq 70$	2,5 1,7 1	0,17 0,17 0,17
ESL ETL	all thicknesses	1 1	0,1 0,1

Sampling and dimensions of test pieces:

Test pieces width b : ES $b = 50$ mm
 ET $b = 2$ tubes and 3 webs (see figure)

Test pieces length L_i : ES $L_i = 120$ mm
 ET $L_i = 200$ mm

